

MS Word Export To Multiple PDF Files Software - Please purchase license.
SECTION 1
1.2 Results Summary
Corporation Yard

ACM SURVEY RESULTS

The following homogeneous building material types were sampled as part of this survey conducted May 12, 2004 and June 8, 2004. Results are summarized in the table below:

May 12, 2004

MTL #	MATERIAL DESCRIPTION	LOCATION	F/NF ¹	COND. ²	% ACM	# SAMP.	QUANTITY
01	Drywall system	Room 7A	NF	Good	Drywall = ND JC = ND	3	N/A

June 8, 2004

MTL #	MATERIAL DESCRIPTION	LOCATION	F/NF ¹	COND. ²	% ACM	# SAMP.	QUANTITY
01	6" Black cove base and mastic	Room 9	NF	Good	CB = ND Mastic = ND	3	N/A
02	4" Black cove base and mastic	Room 9A	NF	Good	CB = ND Mastic = ND	3	N/A
03	Drywall	Rooms 9, 10, 10A, and 10B	NF	Good	ND	3	N/A
04	Drywall	Rooms 7, 7A, 7B, and 7C	NF	Good	ND	3	N/A
05	4" Black cove base and mastic	Rooms 7, 7A, 7B, and 7C	NF	Good	CB = ND Mastic = ND	3	N/A
06	Carpet mastic	Room 7C	F	Good	ND	3	N/A
07	Drywall system	Rooms 1, 4, 4A, 5, 5A, 6, and 6A	NF	Good	Drywall = ND Jt cpd = ND	3	N/A
08	4" Black cove base and mastic	Room 6A	NF	Good	CB = ND Mastic = ND	3	N/A
09	Wall and ceiling texture	Room 5A	F	Good	ND	3	N/A
10	4" Gray cove base and mastic	Room 5A	NF	Good	CB = ND Mastic = ND	3	N/A
11	Sink undercoating	Room 1	NF	Good	4% Chrysotile	3	1
12	2' X 4' White fissure ceiling panel	Room 1	F	Good	ND	3	N/A
13	Drywall system	Rooms 8, 8A, 8B, and 8C	NF	Good	Drywall = ND Joint cpd. = 2% Chrysotile	3	1200 SF
14	12" X 12" Light tan with grey floor tile and mastic	Rooms 10A and 10B	F	Good	FT = 3% Chrysotile M = ND	3	125 SF

* Reviewed Jan. 2006- no changes have been made to the above tables.

Assumed Materials

	MATERIAL DESCRIPTION	LOCATION	F/NF ¹	COND. ²	% ACM	# SAMP.	QUANTITY
	Firedoors/frames	Entrance	NF	Good	Assumed	0	1
	Grout (ceramic tile)	Restroom	NF	Good	Assumed	0	400 SF
	Vapor barrier	Restroom	NF	Good	Assumed	0	400 SF
	Mirror mastic	Restroom	NF	Good	Assumed	0	2 SF

¹ F = Friable; NF = Non-friable Friability is further defined in section 4.
² Cond. = Condition Of Materials Either good, fair or poor.

* Bay Area Air Quality Management District – identifies this material as friable for renovation and disposal purposes.

ND = None Detected
N/A = Not Applicable

SF = Square Feet